

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 14777 LOT 33737

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

<u>50</u>	<u>71</u>	<u>3550</u>		

STUMP

TOTAL NET WT. 3550 PKG. N-CODE 1135

PROD. SPVR.

DATE

WHSE. OPER.

AP 11/15/80

23

240 CG 03 CODE KY-787-D PKG.
 → JAN 11 33737
 EST. WGT. 1090 LBS.

OK BAGS
 OK H

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	
MAKING NOTES	

REMARKS

Total Wgt. 3490#

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-12-80				STARTED	3:45 PM				
TIME	2:50 PM				CAKES USED	46				
RELEASED BY	E.N.				WATER ON	6 AM				
PRESS	22	23	24	25	HRS. WASHED	4				
NO. OF CAKES	46	46	46	52	OHMS	4000				
PRESS with					HRS. WASHED					
WASH TO 2000					OHMS					
TEST AFTER 2					HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION	6				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
 DELIVER TO ctl for color

SAMPLED BY 469

RELEASED BY J.K.

-DRYING-

Dry 12 hrs at 220°F.
 Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
 DELIVER TO

NO. CARS PULLED
 SAMPLED BY

No. Drums 14
 LUMP WGT. 3540
 RELEASED BY J.K.

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
 MAX. TEMP. 150 °F

SCREEN RPM
 MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
 SAMPLES 1 ENV & 1 Pt. can
 DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050093254

N 26174.01

✓

337272
122472
21172

2.67
2.67 -
2.52
2.62 -
2.62
2.61 -
2.61
2.72 -
2.72
2.72 -
2.72
2.73 -
2.73
2.71 -
2.71
2.71 -
2.71
2.71 -
2.69
2.69 -
2.65
2.65 -
2.62
2.62 -
2.60 T

14 DRUMS