

Luciflaint Super Enamel
Interior Trim Enamel
White
A-3139
First

Actual
3/31/42

Market
3/31/42

Pigment							
1901-R Titanium Oxide	1800	55.440	15.63	281.34	14.80	256.4	
EL-290 Ultra. Blue Base	6	.630	26.92	1.62	26.92	1.6	
Vehicle							
(2109) Long Oil Alkyd	2694	336.660	16.54	445.59	15.96	429.9	
(2830) Mixing Varnish	612	82.498	10.43	85.85	11.02	67.4	
(3020) Enamel Solvent	942	140.841	1.79	16.86	2.66	25.0	
(4092) Drier	30	3.732	32.04	9.61	31.00	9.3	
(4091) Drier	18	2.165	13.84	2.49	16.25	2.9	
(3071) Zinc Res. Solution	60	7.272	7.47	4.48	7.25	4.3	
(1767) Anti-Skinning Agent	36	5.332	5.79	2.08	5.74	2.0	
				827.90		809.1	

6198 634.260 155.11 132.0.

634.260
3.40%
612.75

1.351 1.3:

.031 .02
.071 .07
1.453 1.42
.187 .18

1.640 1.61

C.L.	L.C.L.
3.00	3.16
2.55	2.69
	5.00
3.00	3.16
	3.33

OVER 500
UNDER 500

OPA

EE000758

N 4765