7-30-59

TO
T.N. DALTON

RE Customer Complaint
Tremco Products
Cleveland District Office
Aroclor 1254 - Lot B60

Our Analytical Laboratory is not familiar with a viscosity system in Z2 and Z4 units. However the analysis of Lot B-607 shows that Viscosity is within specification. The specification for viscosity for Aroclor 1254 is 44-48 Saybolt Second units at 210°F. This lot analyzed 47.6 SSU at 210°F which is on the high side of the specification range.

If further action is needed it is suggested that the customer send a 16 ounce sample to our Analytical Laboratory for a Viscosity recheck

E E Martin

0200192

TOWOLDMON0054035