

C

1.22 +
1.16 +
1.31 +
1.19 +
1.22 +
1.28 +
1.21 +
1.29 +
1.21 +
1.22 +
1.29 +
1.30 +
1.23 +
1.29 +
1.27 +
1.31 +
1.28 +
1.21 +
1.28 +
1.27 +

020

25.04 ±

PRODUCT NAME MONASTRAL RED Y

DATE PRINTED: 9/28/82

CG 16 RT-759-D PKG

PROCESSES 1 APPROVED BY
RT-759-D (L) BBK 12/17/81

SEP 28 1982

K2173

MI
282

DATE (LOT)

TOTAL EST. WT. 2546 LBS.

COMTYP JOB NAME: 16RT759DPL

NOTES:

INSTRUCTIONS

= PRESSING =

RECORD

VAT	282			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	9-30			STARTED	7:30				
TIME	4:30			CAKES USED	60				
RELEASED BY				WATER ON	10PM				
PRESS	38	39	MI	HRS. WASHED	4				
NO. OF CAKES	60	60	60	OHMS	10+				
PRESS WITHOUT AGITATION				HRS. WASHED					
WASH TO 4000 OHMS WITH 35-75°F WATER				OHMS					
TEST AFTER 3 HOURS				HRS. WASHED					
LOAD ON 8 CARS				OHMS					
				CAKE CONDITION					
				NO CARS LOADED	2+7				
				EXPLAIN LOSSES					

SAMPLES JAR
DELIVER TO

bll

COLOR VERY ~~STICKY~~ STICKY + GUMMY
FULL CAKES HANGING ONTO ~~ED~~ FRAMES
SAMPLED BY
RELEASED BY L.K.

= DRYING =

DRY 18 HOURS AT 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED
DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO CARS PULLED
SAMPLED BY
RELEASED BY LblNO DRUMS
LUMP WGT 2594

= GRINDING =

MILL #1 LSP 1/8" RP SCREEN 1750 RPM
MAX. TEMP 140 DEG F
INERT MILL WITH CO2 WHEN GRINDING
PER OP #0043.SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 FT CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BYSampled
10/4/82

73
51
17

0.00 *
1.53 +
0.14 -
1.80 +
0.14 -
1.54 +
0.14 -
1.58 +
0.14 -
1.63 +
0.14 -
1.65 +
0.14 -
1.57 +
0.14 -
1.62 +
0.14 -
1.66 +
0.14 -
1.69 +
0.14 -
1.69 +
0.14 -
1.68 +
0.14 -
1.53 +
0.14 -
1.57 +
0.14 -
1.62 +
0.14 -
1.60 +
0.14 -
1.61 +
0.14 -
0.89 +
0.14 -
25.94 *