

Aroclor 1242 E1

✓ SC

It is well known that the working life of a.c. paper capacitors impregnated with askarels can be extended by the addition to the askarel of small amounts of suitable epoxy compounds, known as 'scavengers'. This effect is especially beneficial in the case of capacitors operating under arduous service conditions, such as those subjected to frequent surges.

However, some epoxy compounds have been found to be very difficult to control under the practical conditions obtained in existing capacitor impregnation plants.

Aroclor 1242 E1 consists of electrical quality Aroclor 1242 to which a specially purified epoxy compound has been added at just above the concentration at which it will be used. This product has been developed to provide convenient processing in the capacitor impregnation plant as well as sufficient activity to give an effective scavenging action in the finished capacitor.

The vapour pressure of the additive itself is very much lower than that of Aroclor 1242 so that the concentration of the additive will not be reduced during the degassing stage of the process when this is carried out over the usual ranges of temperature and pressure.

The concentration of the additive will be slightly reduced by a batch treatment process with Fullers' earth or other adsorbent. In order to allow for this reduction, the initial concentration of the additive has been set at a slightly higher level than would otherwise be necessary. In this way, after a batch treatment with an adsorbent of normal activity at a concentration up to about 1% by weight, the final concentration of the additive will be sufficient to give protection to the capacitors.

If the impregnant is purified by percolation through a refining column the additive will be initially heavily depleted by the adsorbent. However, the adsorbent later becomes 'saturated' with the additive whilst continuing to remove ionic impurities from the impregnant. The volume of impregnant required to saturate the adsorbent depends upon its mass and activity.

The properties of Aroclor 1242 E1 (see Table 1) are the same as those of Aroclor 1242 except for the following:

Scavenger Content: equivalent to 1.9 to 2.1 mg HCl/g
Dissipation Factor (tan δ) at 100°C, 50 Hz: < 3%
Resistivity at 100°C, 500V, 1 min.: > 1 T Ω cm.

The information contained in this publication is, to our best knowledge, accurate; but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. Monsanto Company, its subsidiaries, associates and affiliates disclaim any liability for loss or damage incurred in connection with the use of the following material. Moreover, nothing contained herein is to be construed as a recommendation to use any product in conflict with any patent.

The information, recommendations and suggestions made herein are offered in the light of prevailing legislation and on the basis of present scientific information (1972) available to Monsanto.

Monsanto

0151638

TOWOLDMON0023863

Table 1

Aroclor 1242 E1. Tentative Data

PROPERTY	TEST METHOD	UNITS	VALUE
Appearance	ASTM D 1702	—	clear liquid free from suspended matter and sediment.
Colour	ASTM D 1702	APHA	50 max.
Density at 20°C	ASTM D 1810 & ISO/R 649	g/cm ³	1.38 to 1.39
Refractive Index at 20°C	ASTM D 1807	—	1.6250 to 1.6270
Kinematic Viscosity at 20°C	ASTM D 446	cSt	55 to 71
Flash Point	ASTM D 92	°C	153 min.
Fire Point	ASTM D 92	°C	none to boiling point.
Pour Point	ASTM D 97	°C	-18 max.
Neutralization No.	Monsanto	mg KOH/g	0.01 max.
Inorganic Chlorides	ASTM D 1821	ppm	0.05 max.
Water Content	ISO/R 760	ppm	30 max.
Hydrolyzable Chlorides	ASTM D 2441	ppm	1.0 max.
Scavenger Content	Monsanto (Appendix 1)	mg HCL/g	1.9 to 2.1
Volume Resistivity at 100°C, 500V, 1 min.	Monsanto	T Ω cm	> 1 min.
Dissipation Factor (tan δ) at 100°C, 50 Hz	Monsanto	%	< 3 max.
Relative Permittivity at 100°C, 50 Hz	Monsanto	—	4.7 to 4.9

A suitable method for estimating the scavenger content is given on page 3. It has sometimes been found difficult to clean the dielectric test cells that are used to measure the dissipation factor and resistivity of epoxide-containing askarels. We have found that it is helpful first to standardize the cell with pure Aroclor 1242 whose dissipation factor is already known. If this measurement is satisfactory, the cell is then rinsed twice with Aroclor

1242 E1 and the measurement proceeds in the usual way.

This product should be treated from the toxicity and safety aspects in the same way as Aroclor 1242 (see Appendix 2). For further information contact Monsanto at 10-18 Victoria Street, London SW1H 0NQ, Telephone 222 5678 or at Place Madou 1, 1030 Brussels, Telephone 19.11.01.

Test Method for determining the quantity of hydrogen chloride scavenging additive in Aroclor

1. Principle

The method involves titrating the oxirane oxygen in glacial acetic acid with a standard perchloric acid solution to a crystal violet end-point. The titration is carried out in an excess of quaternary ammonium bromide, which, on contact with perchloric acid, produces hydrogen bromide. The hydrogen bromide, in turn, reacts with the oxirane oxygen.

2. Reagents

- Glacial acetic acid
- Chloroform
- Perchloric acid solution—0.1 N in glacial acetic acid (standardize against potassium hydrogen phthalate).
- Crystal violet—1% solution in glacial acetic acid.
- Tetraethyl ammonium bromide solution—dissolve 100 g in 400 cm³ of glacial acetic acid.

3. Apparatus

- 10 cm³ burette
- Usual laboratory glassware

4. Procedure

- Weigh 2.5 to 3.0 of the askarel to the nearest 0.05 g into a 125 cm³ Erlenmeyer flask.
- Add 10 cm³ of chloroform, 40 cm³ of glacial acetic acid and 10 cm³ of the tetraethyl ammonium bromide solution and swirl to dissolve.
- Add 1 drop of crystal violet indicator and titrate with 0.1 N perchloric acid to the greatest colour range (violet to green-blue).

5. Calculation

Hydrogen chloride equivalence (mg/g) = $\frac{36.5 \times T \times N}{W}$

where T = titre of perchloric acid (cm³)

N = normality of perchloric acid

W = weight of sample (g)

6. Additional Notes

- The titrant is very stable and does not require frequent restandardization.
- No blank correction should be required if good quality reagents are used.

Storage, Handling and Disposal of Aroclor

Caution

Aroclor contains POLYCHLORINATED BIPHENYLS (PCB's) which some studies have shown may be persistent, an environmental contaminant and, possibly, injurious to certain forms of bird, aquatic and animal life.

Drums

Inside storage is recommended to prevent contamination of the product by water. If the drums have to be stored outside they should be stacked on their sides to prevent water accumulating around the bungs and being breathed into the drum during severe ambient temperature changes.

Drum storage areas should be organised so that any leakages are collected for safe disposal.

Partially emptied drums should not be left open to the air.

Bulk

The supply of Aroclor in bulk tank car loads, offers many advantages to medium and large volume users, compared with drum deliveries. Unloading, storing and transferring to the production unit is safer, easier, faster and cheaper. Material losses due to spillage and incomplete emptying of drums are eliminated. The possibility of product contamination during handling is greatly reduced.

Even where storage and handling facilities are not at present available, the economics of bulk handling may quickly pay for the tanks and piping systems required.

A booklet indicating the type of system necessary for the efficient handling of Aroclor in bulk is available from Monsanto.

As soon as a changeover to bulk delivery is contemplated, experienced Monsanto personnel will be available for site discussions regarding the most efficient type of installation for the particular location and an offloading procedure appropriate to that particular installation.

Handling Precautions

Aroclor drums and containers carry the following label which gives general instructions for handling:

IMPORTANT

CHLORODIPHENYLS (42%-54%) (or 60%) (PCB)

This product contains POLYCHLORINATED BIPHENYLS (PCB's) which some studies have shown may be persistent, an environmental contaminant and, possibly, injurious to certain forms of bird, aquatic and animal life.

PREVENT ANY ENTRY INTO THE ENVIRONMENT THROUGH SPILLS, LEAKAGE, DISPOSAL, VAPOURISATION, RE-USE OF CONTAINERS OR OTHERWISE.

SPILLS, LEAKAGES AND WASTE PRODUCT MUST BE COLLECTED.

Use of this product must be restricted to applications which can be controlled so that entry into the environment does not occur and to applications in which it cannot come into contact with food, animal feedstuffs or pharmaceuticals.

HARMFUL SUBSTANCE IF TAKEN INTERNALLY OR IF IN PROLONGED CONTACT WITH THE SKIN. CAUSES IRRITATION OF SKIN AND EYES.

DURING SHIPMENT AVOID SPILLS AND LEAKAGE INTO INLAND WATERWAYS AND THE SEA.

Store away from food, animal feedstuffs and pharmaceuticals.

Keep container tightly closed.

Do not eat or smoke when using.

Avoid breathing vapours, mist or fumes.

Do not wear contaminated clothing.

Wash product from skin with soap and water.

Wash eyes by flushing with water.

In addition to the foregoing we can add that:

1. Animal toxicity tests (small mammals) indicate that acute oral toxicity is low but that acute dermal toxicity may be moderate.
2. When handling the fluid minimise contact with the skin and wash any off with soap and water. People with sensitive skins should wear gloves resistant to chlorinated solvents or apply a silicone hand cream.
3. Should Aroclor accidentally splash or be rubbed into the eyes, they should be rinsed thoroughly with water for a few minutes. It is suggested that all operators be provided with safety glasses as Aroclor will cause pain if it gets into the eyes.
4. Elementary rules of hygiene should be applied—such as not smoking, eating or drinking during handling and contaminated clothing should be discarded.
5. Aroclor should be handled at ambient temperatures in well ventilated areas. If hot Aroclor has to be handled, a respirator with an active carbon canister should be worn.

Disposal of empty drums and waste Aroclor

Empty drums should not be re-used for anything except scrap Aroclor. Unwanted empty drums should be disposed of by a specialised waste disposal contractor familiar with PCB's who will crush the drums and bury them on an approved toxic dump in accordance with local regulations. Handling of Aroclor in bulk will minimise the problems associated with handling of drums. Waste Aroclor should be disposed of by special high temperature incineration at 1000°C minimum with a residence time of 1.5 seconds or longer or alternatively by a method conforming to local regulations.

Care must be exercised during such disposal and the ultimate use of Aroclor to avoid pollution, particularly of sewers and waterways.

Monsanto Chemicals Limited
10-18 Victoria Street
London SW1H 0NQ
Telephone: 01-222 5678
Telex: 916093

Monsanto Europe S.A.
Place Madou, 1
B-1030, Brussels, Belgium
Telephone: (02) 19.11.01
Telex: 22110/21986

Tentative Sales Specification

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Colour	ASTM D 1702	50 max.
Clarity	ASTM D 1702	Clear
Density at 20 °C (kg/m ³)	ASTM D 1810/ISO R649	1365 - 1380
Refractive Index at 20 °C	ASTM D 1218	1.6225-1.6255
Viscosity at 20 °C (cstks)	ASTM D 445	65 max.
Fire point	ASTM D 92	None to boiling
Pour point (°C)	ASTM D 97	- 18 max.
Neutralisation number (mg KOH/g)	Monsanto	0.01 max.
Inorganic Chlorides (ppm)	ASTM D 1821	0.1 max.
Water content (ppm)	ASTM D 1533/ISO R760	30 max.
Hydrolysable Chlorides (ppm)	ASTM D 2441	1.0 max.
Thermal stability (ppm)	ASTM D 1936	0.5 max.
Penta and higher Chlorinated Biphenyls (%)	CIGRE Method	3.5 max.
Scavenger Equivalent (mg. HCl/g.)		1.5 - 1.8
Volume Resistivity at 100 °C, 500 v. 1 min. (G ohm.cm)		10 min.
Dissipation Factor at 100 °C, 50Hz		0.04 max.
Permittivity at 100 °C and 50 Hz	Monsanto	4.7 - 5.1

Brussels, 15/04/75

The information in this bulletin is to our best knowledge true and accurate but all instructions, recommendations or suggestions are made without guarantee. Since the conditions of use are beyond their control, Monsanto Company and its subsidiaries disclaim any liability for loss or damage suffered from use of these data or suggestions. Furthermore no liability is accepted if use of any product in accordance with these data or suggestions infringes any patent.