NEVADA TESTING LABORATORIES, LTD.

300 WEST BOSTON AVENUE
LAS VEGAS, NEVADA 89102
TELEPHONE 382-1488

TESTING
INSPECTING
RESEARCH
DEVELOPMENT

MEMBER OF
AMERICAN SOCIETY FOR
TESTING MATERIALS

LABORATORY NO. A-569

DATE June 8, 1977

SAMPLE Talc

MARKED None

DATE RECEIVED 5-19-77

SUBMITTED BY: Mr. Ray O'Neal
4896 Powell
Las Vegas, Nevada 89109

Myron Kenyon
1200 Dana #8
Fairfield, Calif. 94533

REPORT OF DETERMINATION

A portion of the sample was weighed, treated with concentrated hydrochloric acid and the insoluble portion was then filtered, washed and ashed. The remaining material was weighed and examined microscopically (150-600X). The results are given below:

Sample Designation	Percent Acid Insoluble, non-organic	Miscroscopic Examination
A-569	86%	less than 1% asbestos-like fibers present

Conclusion:

The sample had less than 1% asbestos-like fibers present (wt./wt basis estimate based on microscopic examination).

Respectfully submitted,

NEVADA TESTING LABORATORIES, LTD.

By: Robert L. Powell

Robert L. Powell, Chemist

RLP:dw

Protected Document--Subject to Protective Order