

10-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 11-808-1 LOT 33706

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	<u>19</u>	<u>2553</u>	<u>35</u>	

TOTAL NET WT. 2553 PKG. N-CODE _____

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

RP 1/16/80 74

1	5	5
1	4	5
1	5	5
1	3	5
1	3	5
1	3	5
1	3	5
1	4	0
1	4	0
1	4	0
1	3	0
1	3	0
1	5	7
1	4	7
1	9	0
1	4	7
1	4	7
1	7	7
1	7	7
1	5	5
1	5	5

36
103
CO 46 CODE YT-808-D PKG.
JAN 12 33706 JAN 12
EST. WGT. 2238 2573 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

36
105

PROCESSES YT-808-D (D)	APPROVED BY EWK 9/28/77 BBK 10/17/77 DCG 10/17/77
TYPED BY JIC 10/26/77	
MAKING NOTES	

REMARKS

NAME: DALAMAR® YELLOW BLENDING

INSTRUCTIONS				-PRESSING-	RECORD					
AT				105	PRESS/LOAD	1ST	2ND	3RD	4TH	5TH
DATE				1-13-80	STARTED	11:30 AM				
TIME				10:30 AM	CAKES USED	68				
RELEASED BY				PR	WATER ON	9:30 AM				
PRESS	32	33	35	36	HRS. WASHED					
NO. OF CAKES	60	62	60	68	OHMS					
PRESS WITHOUT					HRS. WASHED					
WASH TO	4000				OHMS					
TEST AFTER	4				HRS. WASHED					
LOAD	on 9 cars				OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	17				
					EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

DRY 24 HOURS AT 200°F	LUMP: - OK - WET - SALTS - CONTAMINATE
10%	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES DELIVER TO	NO. CARS PULLED SAMPLED BY
	NO. DRUMS LUMP WGT. 2539 RELEASED BY

-GRINDING-

MILL 4 or 10 HSP 1/8" RBCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 190 °F	MAX. TEMP.	°F
	EXPLAIN LOSSES	
SAMPLE WITHOUT MIXING	DATE MIXED 7-16-80	
SAMPLES 1 ENV + 1 Pint can	SAMPLED BY	RELEASED BY
DELIVER TO C T L		

0.00 *

33706

51

231

0.00 *

1.80 +

0.14 -

1.90 +

0.14 -

1.75 +

0.14 -

1.75 +

0.14 -

1.80 +

0.14 -

1.83 +

0.14 -

1.75 +

0.14 -

1.75 +

0.14 -

1.75 +

0.14 -

1.70 +

0.14 -

1.85 +

0.14 -

1.70 +

0.14 -

1.80 +

0.14 -

1.80 +

0.14 -

1.80 +

0.14 -

0.90 +

0.14 -

25.39 *

DUP050293321

N33110.03