



ESTABLISHED 1899

PRODUCT DATA

PLAINTIFF'S

EXHIBIT NO. P-24
FOR IDENTIFICATIONDATE 3/29/95 RPTD PK

618 TALC (B.C.)

Typical Chemical Analysis:

		Percent
<u>Silica</u>	SiO ₂	55-59
Calcium Oxide	CaO	0.4-1.2
Aluminum Oxide	Al ₂ O ₃	
Magnesium Oxide	MgO	30-32
Iron Oxide	Fe ₂ O ₃	0.3-0.6
Moisture	less than	0.6
Loss On Ignition	less than	5.0
Water Solubles	less than	0.1
Acid Solubles	less than	6.0
Water Soluble Iron		None
pH		8.8-9.6

Typical Physical Properties:

Dry Brightness	81-86
Specific Gravity	2.69
Tapped Density, lbs./cu.ft.	58-62
Loose Density, lbs./cu.ft.	24-28
Lbs./solid gallon	28.41
One Lb. Bulks, gallons	0.0446
Oil Absorption	41-45
Thru 200 mesh, %	99
Thru 325 mesh, %	92
Slip	Excellent

*Bacteria Controlled, CTFA, "Microbiology of Cosmetics and Toiletries, 1973." Combined count of less than 500 microorganisms per gram and the absence of gram negative bacteria.

C73

PLAINTIFF'S
EXHIBIT
WCD-299