

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 188908 LOT 33963

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1774</u>	<u>1</u>	<u>T-</u>	<u>285</u>	
<u>1775</u>	<u>1</u>	<u>T-</u>	<u>273</u>	

STUMP

TOTAL NET WT. 3549 PKG. N-CODE _____

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

JV 1 12 80 _____

CG 03 CODE KY-908-D PKG.
 → JAN 22 33963
 EST. WGT. 949 LBS.

OK
HP

PROCESSING INSTRUCTIONS: BATCH UNIT

<i>22/244</i>	PROCESSES KY-908-D (D)	APPROVED BY EWK 12/12/77
		DCG 12/14/77
	TYPED BY pri 1/31/78	
	MAKING NOTES	

REMARKS

TOTAL WGT. 3549#

NAME: DROLOR® YELLOW- LIGHT

NON-BLEEDING

INSTRUCTIONS				- PRESSING -		RECORD					
VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED	3 AM				
TIME						CAKES USED					
RELEASED BY						WATER ON					
PRESS	2	22	23	24		HRS. WASHED	2 HRS				
NO. OF CAKES	46	46	46	52		OHMS	2000				
PRESS with						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 2						HRS. WASHED					
LOAD On 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 8 oz Jar
DELIVER TO CIL for color

SAMPLED BY 169 RELEASED BY TDS

- DRYING -

DRY 24 HOURS AT 180 °F	LUMP: - OK - WET - SALTS - CONTAMINATE
	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	NO. DRUMS 13
DELIVER TO	LUMP WGT. 3569
	SAMPLED BY
	RELEASED BY BLL

- GRINDING -

MILL 939 HSP 1/2" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 170°F		MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE / WITHOUT MIXING	DATE MIXED		
SAMPLES 1 ENV & 1 PT Can			
DELIVER TO C T L	SAMPLED BY	RELEASED BY	

DUP050094241

N 26413.01

33963
41
18

0.00

0.00

2.87

0.14

2.96

0.14

2.88

0.14

3.01

0.14

3.09

0.14

2.99

0.14

3.10

0.14

3.06

0.14

2.89

0.14

3.05

0.14

2.80

0.14

2.94

0.14

1.87

0.14

35.69