

28/240

CG 03 CODE KY-787-D PKG. _____

→ DEC 11 80 38247

EST. WGT. 4090 LBS.

OK/H

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-787-D (Q)	APPROVED BY EWK 9/22/76 DCG 9/27/76
RETYPE BY CJH 4/2/80	
MAKING NOTES	

REMARKS

3338

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	12-12-80					STARTED					
TIME	4:04					CAKES USED					
RELEASED BY	22					WATER ON					
PRESS	46	23	24	25		HRS. WASHED					
NO. OF CAKES	46	46	52	48		OHMS					
PRESS WITH						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 2						HRS. WASHED					
LOAD ON 6 CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY

RELEASED BY

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 14
LUMP WGT. 3341
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT. CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

38247
41
197

0.00 *

0.00 *

2.79 +

0.12 -

2.79 +

0.12 -

2.54 +

0.12 -

2.41 +

0.12 -

2.64 +

0.12 -

2.65 +

0.12 -

2.61 +

0.12 -

2.55 +

0.12 -

2.62 +

0.12 -

2.48 +

0.12 -

2.49 +

0.12 -

2.68 +

0.12 -

2.39 +

0.12 -

1.45 +

0.12 -

33.41 *

0.00 *

14