

E. M. HORN, 11554310



NO CONTRACT OR GUARANTEE SHALL BE BINDING UNLESS CONFIRMED IN WRITING BY AN OFFICER OF THE : WSA

IN REPLY
PLEASE REFER TO

QUOTATIONS SUBJECT TO CHANGE WITHOUT NOTICE AND BASED UPON PRESENT RATES OF FREIGHT. ALL STATEMENTS OR AGREEMENTS CONTAINED IN THIS LETTER ARE CONTINGENT UPON OTHERS FIRST AGREEING OR ANY OTHER RAISED BEYOND OUR CONTROL. CLEVELAND SERRIOS SUBJECT TO CORRECTION.

QPA 26613

EXTERIOR HOUSE PAINT

<u>Pigment</u>	Formula Before Change Pounds	Formula After Change	Before Change Yield in	After Change Gls.	Before Change Unit Cost	After Change Cost	Before Change Total	After Change Cost
Basic Carbonate White Lead.....	285.8	0.0	5.06	0.0	.085		24.29	
Zinc Oxide.....	309.2	254.3	6.66	5.48	.07	.07	21.64	17.8
Asbestine.....	181.8	101.5	7.63	4.26	.01	.01	1.82	1.0
Titanium Dioxide.....	56.1	71.1	1.66	2.03	.145	.16	8.42	11.3
Barytes.....	70.4	0.0	1.89	0.0	.018	.0	1.27	0.0
Sublimed Lead.....	167.0	592.0	3.13	11.1	.07	.07	11.69	41.4
<u>Vehicle</u>								
Refined Linseed Oil.....	440.0	207.0	56.85	26.71	.134	.144	58.96	29.31
Bodied Linseed Oil (indicate viscosity) Z 4.....	88.0	207.0	11.0	25.87	.153	.153	13.46	31.5
Driers.....	8.3	7.0	.88	.8	.153	.153	1.27	1.0
Varnolene.....	55.8	155.0	5.35	23.66	.017	.017	.95	2.6
Calculated yield.....	1664.4	1531.9	100.11	99.91			143.77	136.8
Manufacturing less 2 1/2%								
Actual Yield.....	1622.81	1493.6	97.61	97.41				
Material cost per gallon.							1.47	1.4

A.C. HORN COMPANY, Horn Building, Long Island City, New York.
May 14/43.

REPRODUCED AT THE NATIONAL ARCHIVES

OPA 26614

N 4412.01