

SCHEDULE 1
GRADE SPECIFICATIONS
COST AND SELLING PRICES AS OF MARCH 31, 1942
CON FERRO PAINT & VARNISH CO.

RADE NAME: Ferro Bond
 ATEGORY: Interior Gloss Paints
 OLOR: White
 UMBER: 4806
 UALITY: First

	<u>LB.</u>	<u>GALLONS</u>	<u>UNIT COST</u>	<u>TOTAL COST</u>
IGMENT: 30.8%				
Tit Dioxide	120	3.70	14.78 P H LBS	17.74
Titantad Lithopone	80	2.25	5.68	4.54
CHICLE: 69.2%				
Diamond "K" Linseed Oil	81	10.00	101.85 P H GAL	10.19
Mineral Spirit	26	4.00	8.07	.32
Lacquer Solution Ester	39.50	5.00	55.00	2.75
Lacquer Solution Ester	118.50	15.00	55.00	8.25
Varnish	178.80	24.00	97.00	23.28
2% Cut Cobalt Drier	3.50	.50	79.18	.40
Cut Manganese Drier	1.75	.25	39.69	.10
				2.68
cg., Rec. & Handling				2.68
culated Yield	649.05	64.70		70.25
ufacturing Loss 2%		1.29		
tual Yield		63.41		

T ANALYSIS:

erial Cost Per Gallon or Pound (Total Cost Divided by Actual Yield).....	.70
ufacturing Expense.....	.07
k Cost Per Gallon, or Pound.....	.77
plate Package Cost Per Gallon, or Pound (Container Plus Filling Expense)...	.16
ory Cost in Package Per Gallon, or Pound.....	.93

PRICES

Show the Highest Net Unit Price which was charged or which would have been charged in March 1942, to each of the following types of buyers or transferees:

- (A) To a Company owned or controlled outlet
 (B) To an Independent Whol. saler
 (C) By Company owned or controlled outlet to Retail Customer
 (D) To an Independent Retailer (Dealer)
 (E) To Other (Specify)

\$1.95