

CODE YE-698-D PKG

PROCESSES APPROVED BY
YE-698-D (R) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPR

LOT

MAY -0.81-E 1497

EST'D WGT 3371

TOTAL EST'D WGT= LBS (CRT ENTRY)

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 91 92 93
NO. OF CAKES 32 42 32 32
PRESS WITH AGITATION
WASH TO 2000 OHMS 35-74 F WATER
TEST AFTER 2 HOURS
LOAD ON 4 CARS

1ST	2ND	3RD	4TH	5TH
PRESSLOAD				
STARTED	1234			
CAKES USED	50			
WATER ON	50			
HRS. WASHED	32			
OHMS	7000			
HRS. WASHED				
OHMS				
HRS. WASHED				
OHMS				
CAKE CONDITION				
NO CARS LOADED	5			
EXPLAIN LOSSES				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F LUMP: - OK - WET - SALTS - CONTAMINATED
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 3397

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST GATE AT "9" FOR HIGH
AIR FLOW

RPM
SCREEN
MAX. TEMP.
F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1497
41
17

0.00 *

3.23 +
0.12 -
3.33 +
0.12 -
3.33 +
0.12 -
3.33 +
0.12 -
3.25 +
0.12 -
3.30 +
0.12 -
3.36 +
0.12 -
3.27 +
0.12 -
0.57 +
0.12 -
25.89 *

1497
41
305

0.00 *

25.89 +
3.01 +
0.12 -
3.07 +
0.12 -
2.36 +
0.12 -
33.97 *