

Clear

Mr. J. E. Southwick

March 24, 1972

Mr. S. T. Howell

Strongsville, DPJRC

cc: Mr. R. J. Haviland-#1
Mr. M. W. Malaga -#1
Mr. J. G. Kingston
Mr. W. M. Towne

GLID-TONE HI-GLOSS VARNISH Y-49-A

We are issuing a Y-49 formula with the lead drier removed. We have found that cobalt zirconium is again giving us acceptable dry versus the previous lead drier system. The cost increase will be 1¢ per gallon.

For some time we have been considering the use of anti-skin Orthophen 278, E-258, to achieve better color in the package. The Gardener color which had been 14 maximum will now be 8 maximum. What we had been living with in the past was a cobalt stain problem which was in the wet film and not the dry film. The new anti-skin E-258 will eliminate this problem.

J. E. Southwick

JES/ab

GLD012581