

UNION CARBIDE CORPORATION
INDUSTRIAL HYGIENE DEPARTMENT
P.O. BOX 186 PORT LAVACA,
TEXAS 77979

FACSIMILE TRANSMITTAL COVER LETTER

PLEASE DELIVER THE FOLLOWING PAGES TO:

NAME: Ms. Belia Cortez
FIRM: Union Carbide Corp
CITY: Brownsville, TX
PHONE: (512) 831-4501
FAX: (512) 831-5278

TRANSMITTED FROM:

NAME: Alyce Hambleton (Jack De...)
FIRM: UNION CARBIDE CORPORATION, SEADRIFT PLANT
CITY: PORT LAVACA
PHONE: (512) 553-2091
UNICOM: 8-553-2091
FACSIMILE NUMBER (512) 553-2727

Rec'd 11:20 A.M. 5-15-90

DATE SENT: 5-15-90 TIME SENT: 11:15 AM

TOTAL NUMBER PAGES SENT 10 EXCLUDING COVER PAGE.

IF ALL THE PAGES ARE NOT TRANSMITTED, PLEASE CALL IMMEDIATELY.

OPERATOR'S NAME: ALYCE HAMBLETON PHONE: (512) 553-2091

SPECIAL INSTRUCTIONS: _____

MAY-15-1990 11:18 FROM WEO ChemGas
TO: 10120000000000000000

TO 85188015378 P.01

Kevco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/16/90

TEST METHOD: 40 CFR CH. 1 (1-1-87 EDITION) PT 763,
SUBPT. F APP. A, PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA
ATTENTION: GALT JONES

TX 77979

ANALYST SIGNATURE:

GARY LAMONIE

KEVCO JOB NUMBER:	10402	10402	10402
DATE RECEIVED:	5/14/90	5/14/90	5/14/90
DATE ANALYZED:	5/16/90	5/16/90	5/16/90
CLIENT SAMPLE ID:	01	02	03
PROJECT ID:			
SAMPLE LOCATION:	#6 BOILER (VALVE) ASB. IN MATRIX ONLY	GAS TURBINE	GAS TURBINE (TRANSITION PIECE)
IS THE SAMPLE HOMOGENEOUS?	NO	NO	YES
DOES IT CONTAIN LAYERS?	YES	NO	NO
IS THE SAMPLE FIBROUS?	NO	YES	NO
SAMPLE COLOR:	WHITE/GRAY	TAN	WHITE
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	NO	NO
ASBESTOS TYPE AND PERCENT:	CHRYSTILE 01 - 02		
TOTAL PERCENT ASBESTOS:	TOTAL: 1 - 2	0 PERCENT	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 02 - 10 CELLULOSE 20 - 30	FIBROUS GLASS 30 - 40 CELLULOSE 01 - 05	FIBROUS GLASS 01 - 05 CELLULOSE 01 - 05
NONFIBROUS CONSTITUENTS:	BINDER, MATRIX	BINDER, GLASS SEADS	BINDER
DEVIATION FROM TEST METHOD:	*3		

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*3 SAMPLE RECEIVED WET, DRIED, MATRIX DISSOLVED IN TETRAHYDROFURAN, HEATED, EVAPORATED, THEN ANALYSIS CONTINUES ACCORDING TO TEST METHOD.

Kevco SERVICES INC. • 890 PITTSBURGH ROAD • BUTLER PA 16001
TEL 412-589-6343 FAX 412-566-2172

BRD 1295

MAY-15-1990 11:12 FROM MED ChemGas

TO

85128315278 P.03

Kevco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 753,
SUBPT. F APP. A. PAGES 293-299.REPORT TO: UNION CARBIDE
P.O. BOX 184
PORT LAVACA
ATTENTION: CAL JONES

TX 77979

ANALYST SIGNATURE: Gary Landin

GARY LANDIN

KEYCO JOB NUMBER:	10402	10402	10402
DATE RECEIVED:	5/14/90	5/14/90	5/14/90
DATE ANALYZED:	5/14/90	5/14/90	5/14/90
CLIENT SAMPLE ID:	04	05	06
PROJECT ID:			
SAMPLE LOCATION:	STEAM HEADER (NEXT TO CONTROL ROOM) ASB. IN MATRIX ONLY	FLUE OIL RECIRCULATION DMV	#4 BOILER/TRANSITION PIECE
IS THE SAMPLE HOMOGENEOUS?	NO	YES	YES
DOES IT CONTAIN LAYERS?	YES	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	TAN/WHITE/GRAY	WHITE	TAN
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	NO	NO
ASBESTOS TYPE AND PERCENT:	CHRYSTOTILE 01 - 02		
TOTAL PERCENT ASBESTOS:	TOTAL: 1 - 2	0 PERCENT	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 70 - 80 CELLULOSE < 1%	FIBROUS GLASS 01 - 05 CELLULOSE 50 - 60	FIBROUS GLASS 30 - 40 CELLULOSE 05 - 10
MINERAL CONSTITUENTS:	BINDER, MATRIX, GLASS BEADS	BINDER	BINDER, GLASS BEADS
DEVIATION FROM TEST METHOD:	*1		

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*1 MATRIX OF SAMPLE DISSOLVED IN TETRAHYDROFURAN, HEATED, EVAPORATED, THEN ANALYSIS CONTINUES ACCORDING TO TEST METHOD

Kevco SERVICES INC. • 890 PITTSBURGH ROAD • BUTLER, PA
TEL 412-588-6343 FAX 412-586-2172

BRD 1296

MAY 15 1990 11:10 FROM KCO ChemCos

TO 05120315270 P.04

Kevco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763, SUBPT. F APP. A, PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAYACA
ATTENTION: CAL JONES

TX 7/979

ANALYST SIGNATURE:

Gary Landin
GARY LANDIN

KEVCO JOB NUMBER:	10402	10402	10402
DATE RECEIVED:	5/14/90	5/14/90	5/14/90
DATE ANALYZED:	5/14/90	5/14/90	5/14/90
CLIENT SAMPLE ID:	07	08	09
PROJECT ID:			
SAMPLE LOCATION:	ECONOMIZCA	#4 BOILER VALVE/3RD LEVEL WESTSIDE	#4 BOILER/3RD LEVEL EAST SIDE
IS THE SAMPLE HOMOGENEOUS?	YES	NO	NO
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	WHITE	TAN	TAN
SAMPLE CONTAIN ASBESTOS FIBERS?	NO	YES	YES
ASBESTOS TYPE AND PERCENT:		CHRYTOSILE 05 - 15 AMOSITE 20 - 30	CHRYTOSILE 01 - 05 AMOSITE 40 - 50
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL: 25 - 45	TOTAL: 41 - 59
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 05 - 10 CELLULOSE 40 - 50	FIBROUS GLASS 20 - 30 CELLULOSE 01 - 02	FIBROUS GLASS 01 - 02 CELLULOSE 01 - 02
NONFIBROUS CONSTITUENTS:	BINDER	BINDER, FILLER	BINDER, FILLER
DEVIATION FROM TEST METHOD:		*2	*2

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*2 SAMPLE RECEIVED WET; SAMPLE DRIED PRIOR TO ANALYSIS

MAY-15-1990 11:20 FROM MED ChemGas
KAY 14 190 000 16400 EFF-0178

TO 85126315278 P.05

Kevco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-A7) EDITION: PT 761,
SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA
ATTENTION: CAL JONES

TX 77070

ANALYST SIGNATURE:

Gary Lardini
GARY LARDINI

KEVCO JOB NUMBER:	10402	10402	10402
DATE RECEIVED:	5/14/90	5/14/90	5/14/90
DATE ANALYZED:	5/14/90	5/14/90	5/14/90
CLIENT SAMPLE ID:	10	11	12
PROJECT ID:			
SAMPLE LOCATION:	EVAPORATOR HEADER/ SOUTH	EVAPORATOR HEADER/ BY-PASS VALVE	#2 BOILER HEADER AT DMV
IS THE SAMPLE HOMOGENEOUS?	NO	NO	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	NO
SAMPLE COLOR:	TAN	WHITE/TAN	WHITE
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	NO	NO
ASBESTOS TYPE AND PERCENT:	CHRYSTOLE 20 - 30 AMOSITE < 1%		
TOTAL PERCENT ASBESTOS:	TOTAL: 20 - 30	0 PERCENT	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 20 - 30 CELLULOSE 01 - 02	FIBROUS GLASS 30 - 40 CELLULOSE 05 - 10	FIBROUS GLASS 01 - 05 CELLULOSE 05 - 10
NONFIBROUS CONSTITUENTS:	BINDER, PERLITE	BINDER, FILLER, GLASS BEADS	BINDER, FILLER
DEVIATION FROM TEST METHOD:	*2	*1	

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*2 SAMPLE RECEIVED WET: SAMPLE DRIED PRIOR TO ANALYSIS

*1 MATRIX OF SAMPLE DISSOLVED IN TETRAHYDROFURAN, HEATED, EVAPORATED, THEN ANALYSIS CONTINUES ACCORDING TO TEST METHOD

Kevco SERVICES INC. • 899 PITTSBURGH ROAD • DUISLEN, PA •

TEL 412-585-5343 FAX 412-585-2172

BRD 1298

Kevco

LABORATORY & CONSULTING SERVICES
BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

 TEST METHOD: 40 CFR CH. I (19 OF EDITION) #1 703,
 SUBPT. F APP. A. PAGE 201.700.

 REPORT TO: UNION GARBIDE
 P.O. BOX 186
 PORT LAVACA
 ATTENTION: CAL JONES

ANALYST SIGNATURE:

MARIANNE SAULSBURY

KEVCO JOB NUMBER:	10402	10402	10402
DATE RECEIVED:	5/14/90	5/14/90	5/14/90
DATE ANALYZED:	5/14/90	5/14/90	5/14/90
CLIENT SAMPLE TO:	14	15	16
PROJECT ID:			
SAMPLE LOCATION:	#1 EVAPORATOR	#1 ID FAN	#1 BOILER EXHAUST/ OFF VALVE TO 02
IS THE SAMPLE HOMOGENEOUS?	YES	YES	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	WHITE	GRAY	GRAY
SAMPLE CONTAIN ASBESTOS FIBERS?	NO	YES	YES
ASBESTOS TYPE AND PERCENT:		CHRYSTOTILE 40 - 50 AMOSITE 10 - 20	CHRYSTOTILE < 1%
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL: 50 - 70	LESS THAN 1 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 01 - 05 CELLULOSE 40 50		FIBROUS GLASS 20 - 30 CELLULOSE 01 - 05 HAIR (WOOL) 01 - 05
NONFIBROUS CONSTITUENTS:	BINDER	BINDER	BINDER
DEVIATION FROM TEST METHOD:	#2		

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

*2 SAMPLE RECEIVED WET; SAMPLE DRIED PRIOR TO ANALYSIS

Kevco SERVICES INC. - 850 PITTSBURGH ROAD - BUTLER, PA

TEL 412-206-0343 FAX 412-536-2172

BRD 1299

Kevco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763,
SUBPT. F APP. A, PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA
ATTENTION: CAL JONES

TX 77979

ANALYST SIGNATURE:

M. Saulsbury
MARIAHRE SAULSBURY

KEVCO JOB NUMBER:	10402	10402	10402
DATE RECEIVED:	5/14/90	5/14/90	5/14/90
DATE ANALYZED:	5/14/90	5/14/90	5/14/90
CLIENT SAMPLE ID:	17	18	19
PROJECT ID:			
SAMPLE LOCATION:	BOILER CONTROL HOUSE	AT EVAPORATOR ASB. IN MATRIX MAT.	LINES NORTH OF SERVICE WATER TANK
IS THE SAMPLE HOMOGENEOUS?	NO	NO	YES
DOES IT CONTAIN LAYERS?	NO	YES	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	TAN/GRAY	GRAY	BROWN
SAMPLE CONTAIN ASBESTOS FIBERS?	NO	YES	NO
ASBESTOS TYPE AND PERCENT:		CHRYSTOLE 01 - 02	
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL 1 - 2	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 05 - 10 CELLULOSE 05 - 10	FIBROUS GLASS 05 - 10 CELLULOSE 30 - 40	FIBROUS GLASS 30 - 40
NONFIBROUS CONSTITUENTS:	PERLITE	BINDER	PERLITE
DEVIATION FROM TEST METHOD:			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

Kevco SERVICES INC. • 808 HITTSDORF ROAD • BUTLER, PA 15804
TEL 412-383-0333 FAX 412-556-2172

BRD 1300

Kevco

LABORATORY & CONSULTING SERVICES

RULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763.
SAMPL. & APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA
ATTENTION: CAL JONES

TX 77979

ANALYST SIGNATURE:

MARIANNE SAULSBURY

KEYCO JOB NUMBER:	10402	10402	10402
DATE RECEIVED:	5/14/90	5/14/90	5/14/90
DATE ANALYZED:	5/14/90	5/14/90	5/14/90
CLIENT SAMPLE ID:	20	21	22
PROJECT ID:			
SAMPLE LOCATION:	#3 BOILER/VALVE INSULATION	#1 BOILER 10 FAN	#2 CONDENSATE PUMP
IS THE SAMPLE HOMOGENEOUS?	YES	YES	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	WHITE	TAN	WHITE
SAMPLE CONTAIN ASBESTOS FIBERS?	YES	YES	YES
ASBESTOS TYPE AND PERCENT:	AMOSITE 50 - 60	CHRYSTOTILE 05 - 10 AMOSITE 40 - 50	CHRYSTOTILE 05 - 10 AMOSITE 50 - 60
TOTAL PERCENT ASBESTOS:	TOTAL: 50 - 60	TOTAL: 45 - 60	TOTAL: 55 - 70
FIBROUS MATERIALS AND PERCENT:			
NONFIBROUS CONSTITUENTS:	BINDER	BINDER	BINDER
DEVIATION FROM TEST METHOD: ---			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED WITHOUT THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

MAY-15-1990 11:24 FROM MED ChemGas

TO

85128315278 P.04

Kevco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) Pt 763,
SUBPT. F APP. A. PAGES 293-299.REPORT TO: UNION CARBIDE
P.O. BOX 106
PORT LAVACA,
ATTENTION: CAL JONES

TX 77979

ANALYST SIGNATURE:

M. Saulsbury
MARIANNE SAULSBURY

KEYCO JOB NUMBER: DATE RECEIVED: DATE ANALYZED:	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90	10402 5/14/90 5/14/90
CLIENT SAMPLE ID: PROJECT ID:	23	24	25
SAMPLE LOCATION:	#1 D.A. PUMPS ROOM STEAM INLET	#2 GENERATOR ASS. IN MATRIX UNIT	SPOT #2 TC LOAD RACK
IS THE SAMPLE HOMOGENEOUS?	YES	YES	YES
DOES IT CONTAIN LAYERS?	NO	NO	NO
IS THE SAMPLE FIBROUS?	YES	YES	YES
SAMPLE COLOR:	BROWN	WHITE	WHITE
SAMPLE CONTAIN ASBESTOS FIBERST	NO	YES	NO
ASBESTOS TYPE AND PERCENT:		CHRYSTOLE 01 - 02	
TOTAL PERCENT ASBESTOS:	0 PERCENT	TOTAL: 1 - 2	0 PERCENT
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 10 - 20	FIBROUS GLASS 05 - 10 CELLULOSE 20 - 30 HAIR (WOOL) 10 - 20	CELLULOSE 01 - 02 HAIR (WOOL) 01 - 05
NONFIBROUS CONSTITUENTS:	PERLITE	MATRIX	MATRIX
DEVIATION FROM TEST METHOD:			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT ASBESTOS.

Kevco SERVICES INC. - 870 PINEHURST ROAD - BUTLER, PA 16001
TEL 814/935-5141 FAX 814/935-5142

BRD 1302

Keyco

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 EDITION) PT 763,
SUBPT. F APP. A. PAGES 293-299.

REPORT TO: UNION CARBIDE
P.O. BOX 186
PORT LAVACA
ATTENTION: CAL JONES

TX 77979

ANALYST SIGNATURE:

M. Saulsbury
MARTANNE SAULSBURY

KEYCO JOB NUMBER:	10A02		
DATE RECEIVED:	5/14/90		
DATE ANALYZED:	5/14/90		
CLIENT SAMPLE ID:	26		
PROJECT ID:			
SAMPLE LOCATION:	40# STEAK LINER PART		
IS THE SAMPLE HOMOGENEOUS?	YES		
DOES IT CONTAIN LAYERS?	NO		
IS THE SAMPLE FIBROUS?	YES		
SAMPLE COLOR:	PINK		
SAMPLE CONTAIN ASBESTOS FIBERS?	NO		
ASBESTOS TYPE AND PERCENT:			
TOTAL PERCENT ASBESTOS:	0 PERCENT		
FIBROUS MATERIALS AND PERCENT:	FIBROUS GLASS 01 - 02 CELLULOSE 01 - 02		
NONFIBROUS CONSTITUENTS:	MATRIX		
DEVIATION FROM TEST METHOD:			

- THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN ASBESTOS CONTAINING MATERIAL CONTAINING MORE THAN ONE PERCENT ASBESTOS.

Keyco SERVICES INC. • 830 PITTSBURGH ROAD • BUTLER PA 16001
TEL 412-585-6343 FAX 412-585-2172

BRD 1303

MAY-15-1990 11:25 FROM MFD ChemGas

TO

85128715278

P.06

KEVCO

LABORATORY & CONSULTING SERVICES

BULK ASBESTOS SAMPLE ANALYSIS REPORT

REPORT DATE: 5/14/90

TEST METHOD: 40 CFR CH. I (1-1-87 ED17104) PT 763,
SUBPT. F APP. A. PACS 293-299.

REPORT TO: UNION CARE
P.O. BOX 186
PORT LAVACA
ATTENTION: CAL JONES

TX 77979

ANALYST SIGNATURE:

GARY LANDRUM

KEVCO JOB NUMBER:	10402		
DATE RECEIVED:	5/14/90		
DATE ANALYZED:	5/14/90		
CLIENT SAMPLE ID:	13		
PROJECT ID:			
SAMPLE LOCATION:	#2 BOILER HEADER AT 90 DEGREES		
IS THE SAMPLE HOMOGENEOUS?	YES		
IS THE SAMPLE FIBROUS?	NO		
SAMPLE COLOR:	WHITE		
SAMPLE CONTAIN ASBESTOS FIBERS?	NO		
ASBESTOS TYPE AND PERCENT:			
TOTAL PERCENT ASBESTOS:	0 PERCENT		
FIBROUS MATERIALS AND PERCENT:	FIBROUS CLASS 10 - 20 CELLULOSE 01 - 05		
NONFIBROUS CONSTITUENTS:	BINDER, FILLER		
DEVIATION FROM TEST METHOD:	#2		

THIS TEST REPORT RELATES ONLY TO THE ITEMS TESTED AND MUST NOT BE REPRODUCED EXCEPT WITH THE
APPROVAL OF THE LABORATORY.
- ALL SAMPLES WILL BE DISPOSED OF 90 DAYS FOLLOWING SAMPLE RECEIPT UNLESS OTHERWISE INSTRUCTED BY
THE CLIENT.
- UNDER CURRENT EPA REGULATIONS, AN "ASBESTOS CONTAINING MATERIAL" CONTAINS MORE THAN ONE PERCENT
ASBESTOS

IF SAMPLE RECEIVED WITH SAMPLE LABEL PRIOR TO ANALYSIS

Kevco SERVICES INC • 890 PITTSBURGH ROAD • BUTLER, PA 16001
TEL 412-586-6333 FAX 412-586-2172

BRD 1304