

FORMULA RECORD				FILMED			
Goods: <i>Clear 5 Ringles Stains</i>				Formula No. <i>Y-2700B</i>			
Consistency				Laboratory No.			
For use on				Cost Class.	Date <i>12-29-48</i>		
Customer				Strainer	Grind		
				MB			
Code Number	One Gallon Batch			Large Batch		Is agitator required	
	Flts	Lbs.	Ozs.	Gals.	Lbs.	Wt. or Be	Temp.
<i>D-1</i>	<i>1/2</i>			<i>5 1/4</i>		<i>7H</i>	
<i>D-5</i>	<i>1/2</i>			<i>6 1/4</i>			
<i>D-10</i>	<i>1/4</i>			<i>3 1/8</i>			
<i>D-18</i>	<i>1 3/4</i>			<i>21 1/2</i>			
<i>S-148</i>	<i>5</i>			<i>62 1/2</i>			
						Viscosity	Temp.
						Viscosimeter	
						Color	Sheen
						Non Vol.	Flash Pt. <i>180 F</i>
						Watch for	
						Reducer	
						Amt. for brushing	
						Spraying	Tumbling
						Dipping	Drip Time
						Bake	Temp.
						Air dries in	
						A. D. to recoat in	
						Remarks:	
Standard Formula				DISCONTINUED			
Not to be taken							
from File.							
				SEE <i>Y-1880</i>			
Yield				Formulator <i>J.P. Wagner</i>			

Changed to lower 018
Content

Characteristics and Method of Using		Cost Data				Customers
Type of Gunda						
Color						
Luster						
Match for						
Kind of Reducer						
Amount of Reduction for						
Brushing						all plants 11-5-4
Spraying	Pressure					
Dipping	Drip Time	Analysis				
Floccing	Drip Time	Limeless Oil				14
Tumbling		Refined Crude Oil				28
Air dry to recoat		Mineral Spirits				58
To Sand or Rub						<u>100</u>
Bake Time	Temp.					
Rub with						
Polish with						
Schedule						

GLD059685

494-1021105

Clear Shingle Stain Liquid

Y270017

Date 7-20-34

Laboratory No.

Cost Classification

[illegible]

[illegible]

GLD059688

Creosote Oil Refined	42.55%
Mineral Spirits	57.45

100.00%

Weight per gal. 7.35 lbs.

GLD059689