

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 6-1882 LOT 424

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
<u>1850</u>	<u>1</u>		<u>7-86</u>	
<u>1750</u>	<u>1</u>		<u>7-249</u>	

STUMP

TOTAL NET WT. 3600 PKG. N-CODE _____

PROD. SPVR. _____

DATE

WHSE. OPER. _____

1/17/82

PRODUCT NAME = KROLOR YELLOW LIGHT

DATE PRINTED: 12/21/81

CG 03 CODE KY-788-D PKG

NON-BLEEDING

PROCESSES APPROVED BY
KY-788-D (J) FWF 11/05/81

LOT A2H55

EST. WT. 3489* LBS.

TYPED BY JMH

MAKING NOTES

JOB NAME: 03KY788DPJ

INSTRUCTIONS

= PRESSING =

RECORD

VAT 12401
DATE 1-8
TIME 5:20 AM
RELEASED BY 2371
PRESS 122 23 24 95 96
NO. OF CAKES 46 46 46 40 40
PRESS WITH AGITATION
WASH TO 500 M MHOS WITH 35-75% WATER
TEST AFTER 2 HOURS
LOAD ON 6 CARS

1ST	2ND	3RD	4TH	5TH
STARTED				
CAKES USED				
WATER ON				
HRS. WASHED				
M MHOS				
HRS. WASHED				
M MHOS				
HRS. WASHED				
M MHOS				
CAKE CONDITION				
NO CARS LOADED				
EXPLAIN LOSSES				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 12 HOURS AT 220* F
THEN DRY 8 HOURS AT 160* F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 3559

= GRINDING =

MILL 939HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP 150 DEG F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

55
41
294

0.00

2.23

0.14

2.25

0.12

2.22

0.14

2.24

0.14

2.23

0.14

2.17

0.14

2.24

0.14

2.37

0.14

2.37

0.14

2.50

0.14

2.24

0.14

2.21

0.14

2.35

0.14

2.35

0.14

2.33

0.14

2.07

0.14

1.43

0.14

35.52