

CG 01 CODE YE-698-D PKG -----

LOT

F0007

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

MAKING NOTES

JOB NAME: 01YE698DPS

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

INSTRUCTIONS EC
VAT 242
DATE 5-27
TIME 4:00 PM
RELEASED BY [Signature]
PRESS 2 93
NO. OF Cakes 54 54
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

PRESSING =
PRESSLOAD 1ST 2ND 3RD 4TH 5TH
STARTED 445A
CAKES USED 521
WATER ON 90
HRS. WASHED 3
OHMS 2.100
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION 1+6
NO CARS LOADED
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY [Signature]

= DRYING =
(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY [Signature]
RELEASED BY [Signature]

NO DRUMS 19
LUMP WGT 5687

= GRINDING =
MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

0007

41
17

0.00 *

6

3.15 +
0.12 -/
3.14 +
0.12 -/
3.53 +
0.12 -/
3.14 +
0.12 -/
3.36 +
0.12 -/
1.45 +
0.12 -/
17.05 *

YE 698
0007
41
124

0.00 *

1

13

3.23 +
0.14 -/
3.35 +
0.14 -/
2.92 +
0.14 -/
3.35 +
0.14 -/
3.29 +
0.14 -/
3.10 +
0.14 -/
3.13 +
0.14 -/
3.33 +
0.14 -/
3.11 +
0.14 -/
3.23 +
0.14 -/
3.34 +
0.14 -/
3.19 +
0.14 -/
3.07 +
0.14 -/
39.82 *

17.05

5687