

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG

LOT F2H29

MAY 26 1982

EST. WT. 5547* LBS.

92
1845

AK
1/8

NON-BLEEDING

PROCESSES

YE-698-D (S) F. POST 10/09/81

ALTERNATE

TYPED BY JMH

4/22/82

APPROVED BY

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF Cakes	WASH TO 500 M MHOS WITH 35-75* WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
					54																

SAMPLES 8 OZ
DELIVER TO CTL.

SAMPLED BY
RELEASED BY

Bfl

Bfl

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

DELIVER

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 19
LUMP WGT 5694

AK

CO-GROUND PER CTL INSTRUCTIONS

GRINDING

MILL MIKROATOMIZE SCREEN

RPM

SCREEN

RPM

MAX. TEMP DEG F

MAX. TEMP.

F

SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE

SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

N39448

21
11
11
9
311
12
313
12
312
12
312
12
315
12
317
12
315
12
313
12
313
12
313
12
314
12
310
12
318
12
317
12
317
12
317
12
314
12
111
12
311